

Declaration of Performance

Declaration of Performance in accordance with EU-regulation 305/2011, Annex III

No. 010CPR2013-07-01

1. Unique identification code of the product-type:

Hot rolled structural steel plate S355K2 / 1.0596

2. Type, batch or serial number or any other element allowing identification of the construction product as required under Article 11(4):

Plate S355K2 according to EN 10025-2

3. Intended use or uses of the construction product, in accordance with the applicable harmonized technical specification, as foreseen by the manufacturer:

Welded, bolted and riveted structures

4. Name, registered trade name or registered trade mark and contact address of the manufacturer as required pursuant Article 11(5):

NLMK DanSteel A/S Havnevej 33 DK 3300 Frederiksværk, Denmark Tel. +4547770333 www.dansteel.dk

5. Name and contact address of the authorised representative whose mandate covers the tasks specified in Article 12(2):

Not applicable.

6. System or systems of assessment and verification of constancy of performance of the construction product as set out in Annex V:

System 2+

7. In case of the declaration of performance concerning a construction product covered by a harmonised standard:

Notified factory production control certification body TÜV Nord Systems GmbH & Co. KG No. 0045 conducted an initial inspection of the plant and of the factory production control and performs continuous monitoring and conformity assessment of the factory production control.



8. Declared performance

	red performance				
Essential characteristic		Performance		Harmonised technical specification	
Tolerances	Thickness		In accordance with EN 10029: 2011		
on	Length		In accordance with EN 10029: 2011 In accordance with EN 10029: 2011		
dimensions and shape					
•	Nominal thickness (mm)		Values ReH (MPa)		
	>	≤	min	max	
		16	355		
	16	40	345	7	
Yield	40	63	335	7	
Strength	63	80	325	7	
	80	100	315	\dashv	
	100	150	295	-	
	150	200	285	\dashv	
				Zalaras Dans (MDa)	\dashv
	Nominal thickn			Values Rm (MPa)	
	3	<u>≤</u>	min	max 620	-
		16	470	630	
Tensile	16	40	470	630	
	40	63	470	630	
Strength	63	80	470	630	-
	80	100	470	630	EN 10025-1
	100	150	450	600	:2004
	150	200	450	600	
			Values A5 (%)		
	>	<u> </u>	min	max	
	3	40	20	_	
Elongation	40	63	19	_	
	63	100	18	_	
	100	150	18		
	150	200	17		
Impact	Nominal thickness (mm)		Values (J @ -20°C)		
Strength	>	≤	min	max	
		150	40		
	150	200	33		
	Nominal thi	ckness (mm)		Values (%)	
	>	VI	min	max	
Weldability		30		0,45	
CEV	30	40		0,47	
	40	150		0,47	
	150	200		0,49	
Durability	Nominal thi	ckness (mm)		Values (%)	
(chemical	> ≤		min max		
composition)		16		C: 0,20 S: 0,025	
				Mn: 1,60 N: -	
			4	P: 0,025 Cu: 0,55	_
	16	40		C: 0,20 S: 0,025	
				Mn: 1,60 P: 0,025 N: - Cu: 0,55	
	40		-	C: 0,025 Cu: 0,55 C: 0,22 S: 0,025	\dashv
	40			Mn: 1,60 N: -	
				P: 0,025 Cu: 0,55	

9. The performance of the product identified in points 1 and 2 is in conformity with the declared performance in point 8. This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 4. Signed for and on behalf of the manufacturer by:

Zibrandt Greisen Chief Metallurgist.